

THERMO-OPTICAL PROPERTIES

Thermo-optical properties of common substances in bulk are compiled in Table 1. Table 2 gives a more detailed and specific compilation for typical thermal control surfaces used in spacecraft thermal design, where different values for beginning-of-life conditions and end-of-life conditions are given to account for in-orbit degradation (e.g. by atomic oxygen and oxygen ion chemical attack). In all cases the two-spectral-band model (explained in [Heat transfer and thermal modelling](#)) is assumed.

Table 1. Thermo-optic properties of some common materials (at 288 K).

Substance	Solar absorptance (normal) α	Emissivity (hemispherical, bolometric) ε
Alumina	0.1..0.25	0.3..0.5
Aluminium	0.1..0.15	0.05 ^a
Bakelite		0.94
Beryllium ^b	0.5..0.7	0.18
Brass		0.03..0.1
Copper	0.2..0.5	0.05
Cork		0.7
Elastomer		0.9
Glass (pyrex)		0.9
Glass (quartz)		0.93
Glass (window)	0.1	0.9
Ice	0.3..0.5	0.92
Iron (cast-)	0.3	0.2..0.7
Magnesium		0.2..0.5
Methacrylate		0.9
Nickel	0.2	0.05
Paper	0.3	0.95
Platinum		0.09
Polyethylenab		0.9
Polystyrenab		0.9
Polyurethanab		0.9
PVC ^a		0.9
Sand & soil	0.4..0.7	0.5..0.8
Silicon	0.7	0.3
Silver		0.02
Steel (carbon-)	0.2	0.2..0.6
Steel (stainless-)	0.4	0.2..0.3
Teflon (PTFE)	0.12	0.85
Titanium	0.4..0.7	0.2..0.5
Wolfram	0.45	0.09

^{a)} Aluminium emissivity may vary a lot, from 0.05 if polished, to 0.8 if hard anodised or dew-covered, or even $\varepsilon=0.85$ if black anodised. Solar absorptance also may vary from 0.09 if polished to 0.4 if hard anodised; aluminium foil gets hot under sunshine because $\alpha/\varepsilon=0.15/0.05>1$). Aluminium paint may have $\varepsilon=0.3$ when bright and $\varepsilon=0.6$ when dull.

- b) Emissivity of thin plastic films is much lower than the quoted bulk value (e.g. for 0.1 mm films, $\varepsilon=0.15$ for polyethylene and $\varepsilon=0.60$ for PVC).

Table 2. Thermo-optic properties of typical spacecraft surfaces (at 288 K).

Surface	BOL (Beginning of life)			EOL (End of life)		
	Solar absorptance, α	Emissivity, ε	α/ε	Solar absorptance, α	Emissivity, ε	α/ε
Aluminium anodised (structures)	0.20	0.60	0.33	0.80	0.80	1.00
Aluminium (vessels)	0.15	0.20	0.75	0.10	0.10	1.00
Aluminised kapton (al. inside)	0.40	0.80	0.50	0.40	0.80	0.50
Aluminised kapton (al. outside)	0.15	0.05	3.0	0.15	0.05	3.0
Beta cloth	0.30	0.85	0.35	0.40	0.85	0.47
Black paint (insides)	0.95	0.90	1.06	0.90	0.90	1.00
GFRP (solar panels, structures)	0.85	0.85	1.00	0.85	0.85	1.00
Goldised kapton (gold outside)	0.25	0.02	12	0.25	0.02	12
MLI (back aluminised kapton)	0.30	0.60	0.50	0.60	0.60	1.00
OSR (radiators)	0.08	0.80	0.10	0.08	0.80	0.10
Silver paint (electrically cond.)	0.35	0.45	0.78	0.50	0.60	0.83
Solar cells	0.70	0.70	1.00	0.80	0.80	1.00
Titanium tiodised (apogee motor)	0.60	0.60	1.00	0.60	0.60	1.00
White paint (antenna)	0.20	0.85	0.24	0.60	0.85	0.71